


Appl. No. : 10/522,036  
 Filed : January 19, 2005


### AMENDMENTS TO THE CLAIMS

1. **(Currently amended)** A chemical amplification type positive photoresist composition prepared by dissolving:

(A) a slightly alkali-soluble or alkali-insoluble novolak resin having a property that solubility in an aqueous alkali solution is enhanced in the presence of an acid, comprising either or both of a constituent unit (a1) represented by the following general formula (I):




wherein  $R^1$  represents either an alkylene group having 1 to 10 carbon atoms which may have a substituent or a group represented by the following general formula (II):



Appl. No. : 10/522,036  
 Filed : January 19, 2005

(wherein  $R^4$  represents an alkylene group having 1 to 10 carbon atoms which may have a substituent and  $m$  represents 0 or 1), the alkylene group may have an oxygen bond (ether bond) in the main chain,  $R^2$  and  $R^3$  each independently represents a hydrogen atom or an alkyl group having 1 to 3 carbon atoms, and  $n$  represents an integer of 1 to 3, and an intermolecular crosslinked moiety (a2) represented by the following general formula (III):



wherein  $R^1$  represents either an alkylene group having 1 to 10 carbon atoms which may have a substituent or a group represented by the above general formula (II) (wherein  $R^4$  represents an alkylene group having 1 to 10 carbon atoms which may have a substituent and  $m$  represents 0 or 1), the alkylene group may have an oxygen bond (ether bond) in the main chain,  $R^2$  and  $R^3$  each independently represents hydrogen atom or alkyl group having 1 to 3 carbon atoms, and  $n$  represents an integer of 1 to 3;

(B) a compound generating an acid under irradiation ~~with radiation~~, in an organic solvent, wherein the content of an acid component in the photoresist composition is 10 ppm or less.

2. (Canceled)

Appl. No. : 10/522,036  
Filed : January 19, 2005

3. (Canceled)

4. (Currently amended) The chemical amplification type positive photoresist composition according to ~~any one of claims 1 to 3~~ claim 1, wherein the component (B) is a compound generating an acid under irradiation with i-rays (365 nm).

5. (Currently amended) The chemical amplification type positive photoresist composition according to ~~any one of claims 1 to 3~~ claim 1, which further comprises a basic compound as the component (C).


6. (Original) The chemical amplification type positive photoresist composition according to claim 5, which comprises the component (C) in the amount of 0.01 to 5 parts by weight based on 100 parts by weight of the resin component contained in the resist composition.

7. (Currently amended) The chemical amplification type positive photoresist composition according to ~~any one of claims 1 to 3~~ claim 1, which comprises  $\gamma$ -butyrolactone.

8. (Currently amended) The chemical amplification type positive photoresist composition according to ~~any one of claims 1 to 3~~ claim 1, which is used for a thick-film photolithography process used for forming a resist film having a thickness of about 2 to 7  $\mu\text{m}$ .

9. (Original) The chemical amplification type positive photoresist composition according to claim 8, wherein the thick-film photolithography process is used for forming a resist pattern for implantation.

10. (Original) A method for synthesis of the component (A) of claim 1, which comprises reacting a novolak resin with a crosslinking agent represented by the following general formula (VI):



Appl. No. : 10/522,036  
 Filed : January 19, 2005

wherein  $R^1$  represents either an alkylene group having 1 to 10 carbon atoms which may have a substituent or a group represented by the above general formula (II) (wherein  $R^4$  represents an alkylene group having 1 to 10 carbon atoms which may have a substituent and  $m$  represents 0 or 1, and the alkylene group may have an oxygen bond (ether bond) in the main chain, in the substantial absence of an acid catalyst.


11. (Canceled)

12. (Canceled)

13. (Currently amended) A method for formation of a resist pattern of a thick-film photolithography process, which comprises forming a resist film having a thickness of 2 to 7  $\mu\text{m}$  made of the chemical amplification type positive resist composition of ~~any one of claims 1 to 3~~ claim 1 on a substrate, and subjecting to selective exposure, post exposure bake (PEB) treatment, and development.

14. (Original) The method for formation of a resist pattern according to claim 13, wherein a resist pattern for implantation is formed in the thick-film photolithography process.

15. (Currently amended) A chemical amplification type positive photoresist composition comprising (A2) a resin made of a reaction product of (A1) an alkali soluble resin and (C1) a crosslinking polyvinyl ether compound wherein alkali solubility enhances by an action of an acid, and (B1) a photo acid generator generating acid under irradiation with radiation, wherein the component (A1) comprises a unit ( $a1'$ ) derived from ( $\alpha$ -methyl)hydroxystyrene represented by the following general formula ( $I'$ ):




Appl. No. : 10/522,036  
 Filed : January 19, 2005

wherein R represents a hydrogen atom or a methyl group and l represents an integer of 1 to 3, and an alkali-insoluble unit (a2') having no acid dissociable dissolution inhibiting group, and wherein a dissolution rate of the component (A1) to an aqueous 2.38% by weight solution of TMAH (tetramethylammonium hydroxide) is from 10 to 100 nm/second,

wherein the component (B1) is a poly(bissulfonyl)diazomethane photo acid generator.

16. (Original) The chemical amplification type positive photoresist composition according to claim 15, wherein the constituent unit (a2') is a unit derived from ( $\alpha$ -methyl)styrene represented by the following general formula (II'):



wherein R represents a hydrogen atom or a methyl group, R<sup>11</sup> represents an alkyl group having 1 to 5 carbon atoms and p represents an integer of 0 or 1 to 3.

17. (Original) The chemical amplification type positive photoresist composition according to claim 16, wherein the content of constituent unit (a2') in the component (A1) is from 5 to 35 mol%.

18. (Original) The chemical amplification type positive photoresist composition according to claim 15, wherein the weight-average molecular weight of the component (A2) is from 20000 to 150000.

19. (Canceled)

20. (Canceled)


Appl. No. : 10/522,036  
Filed : January 19, 2005

21. **(Original)** The chemical amplification type positive photoresist composition according to claim 15, which further comprises a nitrogen-containing organic compound (D').

22. **(Original)** A resist pattern forming method, which comprises applying the chemical amplification type positive photoresist composition of claim 15 on a substrate, and subjecting to prebaking, selective exposure, PEB (post exposure bake) and alkali development to form a resist pattern.


23. **(New)** A chemical amplification type positive photoresist composition prepared by dissolving:

(A') a slightly alkali-soluble or alkali-insoluble polyhydroxystyrenic resin having a property that solubility in an aqueous alkali solution is enhanced in the presence of an acid, comprising either or both or a constituent unit (a'1) represented by the following general formula (IV):



Appl. No. : 10/522,038  
 Filed : January 19, 2008

wherein  $R^1$  represents either an alkylene group having 1 to 10 carbon atoms which may have a substituent or a group represented by the above general formula (II) (wherein  $R^4$  represents an alkylene group having 1 to 10 carbon atoms which may have a substituent and  $m$  represents 0 or 1), the alkylene group may have a oxygen bond (ether bond) in the main chain, and an intermolecular crosslinked moiety (a'2) represented by the following general formula (V):



wherein  $R^1$  represents either an alkylene group having 1 to 10 carbon atoms which may have a substituent or a group represented by the above general formula (II) (wherein  $R^4$  represents an alkylene group having 1 to 10 carbon atoms which may have a substituent and  $m$  represents 0 or 1), the alkylene group may have an oxygen bond (ether bond) in the main chain; and

(B) a compound generating an acid under irradiation, in an organic solvent,

Appl. No. : 10/522,036  
Filed : January 19, 2005

wherein the content of an acid component in the photoresist composition is 10 ppm or less.

24. (New) The chemical amplification type positive photoresist composition according to claim 23, wherein the component (B) is a compound generating an acid under irradiation with i-rays (365 nm).

25. (New) The chemical amplification type positive photoresist composition according to claim 23, which further comprises a basic compound as the component (C).

26. (New) The chemical amplification type positive photoresist composition according to claim 25, which comprises the component (C) in the amount of 0.01 to 5 parts by weight based on 100 parts by weight of the resin component contained in the resist composition.

27. (New) The chemical amplification type positive photoresist composition according to claim 23, which comprises  $\gamma$ -butyrolactone.

28. (New) The chemical amplification type positive photoresist composition according to claim 23, which is used for a thick-film photolithography process used for forming a resist film having a thickness of about 2 to 7  $\mu\text{m}$ .

29. (New) The chemical amplification type positive photoresist composition according to claim 28, wherein the thick-film photolithography process is used for forming a resist pattern for implantation.

30. (New) A method for formation of a resist pattern of a thick-film photolithography process, which comprises forming a resist film having a thickness of 2 to 7  $\mu\text{m}$  made of the chemical amplification type positive resist composition of claim 23 on a substrate, and subjecting to selective exposure, post exposure bake (PEB) treatment, and development.


31. (New) The method for formation of a resist pattern according to claim 13, wherein a resist pattern for implantation is formed in the thick-film photolithography process.



Appl. No. : 10/522,038  
 Filed : January 19, 2005

32. (New) A chemical amplification type positive photoresist composition prepared by dissolving:


(A'') a slightly alkali-soluble or alkali-insoluble polyhydroxystyrenic resin having such a property that solubility in an aqueous alkali solution is enhanced in the presence of an acid comprising either or both of a constituent unit (a'1) represented by the following general formula



(IV):

wherein R<sup>1</sup> represents either an alkylene group having 1 to 10 carbon atoms which may have a substituent or a group represented by the above general formula (II) (wherein R<sup>4</sup> represents an alkylene group having 1 to 10 carbon atoms which may have a substituent and m represents 0 or 1), the alkylene group may have an oxygen bond (ether bond) in the main chain, and an intermolecular crosslinked moiety (a'2) represented by the following general formula (V):

Appl. No. : 10/522,038  
 Filed : January 19, 2005



wherein  $R^1$  represents either an alkylene group having 1 to 10 carbon atoms which may have a substituent or a group represented by the above general formula (II) (wherein  $R^4$  represents an alkylene group having 1 to 10 carbon atoms which may have a substituent and  $m$  represents 0 or 1), the alkylene group may have an oxygen bond (ether bond) in the main chain, and a styrenic constituent unit; and

(B) a compound generating an acid under irradiation, in an organic solvent, wherein the content of an acid component in the photoresist composition is 10 ppm or less.

33. (New) The chemical amplification type positive photoresist composition according to claim 32, wherein the component (B) is a compound generating an acid under irradiation with i-rays (365 nm).

Appl. No. : 10/522,036  
Filed : January 19, 2006

34. (New) The chemical amplification type positive photoresist composition according to claim 32, which further comprises ~~a basic compound as the component (C)~~.

35. (New) The chemical amplification type positive photoresist composition according to claim 34, which comprises the component (C) in the amount of 0.01 to 5 parts by weight based on 100 parts by weight of the resin component contained in the resist composition.

36. (New) The chemical amplification type positive photoresist composition according to claim 32, which comprises  $\gamma$ -butyrolactone.

37. (New) The chemical amplification type positive photoresist composition according to claim 32, which is used for a thick-film photolithography process used for forming a resist film having a thickness of about 2 to 7  $\mu\text{m}$ .

38. (New) The chemical amplification type positive photoresist composition according to claim 37, wherein the thick-film photolithography process is used for forming a resist pattern for implantation.

39. (New) A method for formation of a resist pattern of a thick-film photolithography process, which comprises forming a resist film having a thickness of 2 to 7  $\mu\text{m}$  made of the chemical amplification type positive resist composition of claim 32 on a substrate, and subjecting to selective exposure, post exposure bake (PEB) treatment, and development.

40. (New) The method for formation of a resist pattern according to claim 39, wherein a resist pattern for implantation is formed in the thick-film photolithography process.